DuploCOLL® 101

Art. No. 11 805 B 06

Double-sided pressure-sensitive adhesive tape for mounting and permanent bonding on all smooth surfaces

Product construction			
	Name	Colour	Thickness [mm]
Liner	Polyethylene paper	white, printed	approx. 0,130
Adhesive	Pure acrylic		approx. 0,050
		Total thickness:	approx. 0,180

Product advantages

- · Tested and recognized according to UL 969
- The use of a high strength pure acrylic adhesive guarantees maximum resistance to ageing and UV-radiation.
- The adhesive has good to excellent resistance to oil, grease, cooling lubricants, acids, alkaline solutions, disinfectant, fuel and many other chemicals (According to FINAT FTM 17).
- The high initial adhesion (tack) offers high application security immediately after mounting.
- The PE coated release paper increases the transparency of the adhesive film avoids wrinkles at high humidity fluctuations and
 offers excellent die-cutting properties.
- DuploCOLL® 101 meets the requirements laid down in the FMI specification.
- Excellent die-cutting properties
- Easily removable protective liner
- Non-slip liner

Main application fields

- · Mounting of plates, emblems, face plates, decorative trims and scales where a particularly high transparency is required
- Manufacture of membrane switches
- Bonding of product samples and displays in the advertising industry

Product features		Applicability on	
Shear strength	• • •	FR 2 / FR 4 printed circuit board (PCB)	• • •
Initial adhesion	● ● ○	Foam	• 0 0
Final adhesion	• • 0	Rubber	• 0 0
Dimensional stability	• 0 0	Fabric	• • 0
Adhesion on even surfaces	• • •	Glass/Ceramics	• • •
Adhesion on rough surfaces	• 0 0	Wood	● ● ○
Ageing resistance	• • •	High energy plastics: PVC, PC, ABS,	• • •
Weathering resistance	• • •	Low energy plastics: PE, PP,	• 0 0
Chemical resistance	• • •	Metal	• • •
Resistance to plasticizers	● ● ○	Paper/Cardboard	• • 0
● ● very suitable ● ○ suitable	● ○ ○ suitable with reductions	o o not suitable	



DuploCOLL® 101

Art. No. 11 805 B 06

Double-sided pressure-sensitive adhesive tape for mounting and permanent bonding on all smooth surfaces

Specific technical data*

Temperature range -40 °C to +150 °C

Technical Data			1
Shear strength	on steel according to DIN EN 1943, edition 1996, at +23 °C +/- 2°C	40 N/625 mm ²	
Peel strength	on steel according to DIN EN 1939, edition 1996, at +23 °C +/- 2°C	13 N/25 mm	.4 M

Application

Recommended application temperature 18 °C to 35 °C

Application guidelines <u>www.lohmann-tapes.com</u>

Storage

Adhesive tapes should be stored at room temperature and normal humidity (50-70 %).

The storage stability is two years after delivery.

Product presentation					
Converted product	Rolls				
Width [mm]	> 19	> 25	> 50		
Length [m]	50	100	200		
Max. log width: 1000 mm	Other dimensions, die-cuts and sheets on request.				

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.

The physical characteristics contained in our data sheets represent typical or average values. They do not represent any warranties or guarantees and must not be used for technical specification purposes. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. The buyer is responsible for determining the suitability of the specific tape for its intended use in connection with user's method of application. Please consult our Technical Applications Department for specific advice. Our general Term and Conditions of Sale apply, particularly with regard to warranty and liability.

Date of issue: February 2011

Lohmann GmbH & Co. KG Irlicher Strasse 55 56567 Neuwied Germany

Phone: + 49 (0) 26 31 34 - 0 Fax: + 49 (0) 26 31 34 - 6661 E-mail: info@lohmann-tapes.com

For further Information www.lohmann-tapes.com



^{*} Specific test results, statistically not approved.