

# Duplocoll® 370

Art. No. 11 731 I 01

## Double-sided pressure sensitive adhesive mounting tape

### Product construction

	Name	Colour	Thickness [mm]
<b>Liner</b>	Silicone paper	yellow	approx. 0,08
<b>Adhesive closed side</b>	Modified acrylic		
<b>Carrier</b>	PVC film	white	approx. 0,23
<b>Adhesive open side</b>	Modified acrylic		
<b>Total thickness:</b>			<b>approx. 0,31</b>

### Product advantages

- High initial adhesion (tack)
- High shear strength
- Excellent resistance to ageing, weathering and UV-radiation
- Extensive resistance to the influence of chemicals and solvents (domestic cleaning material and polishing agents)
- Due to the high adhesive coating weight the adhesive adapts to surface contours, even on rough surfaces, such as chip board

### Main application fields

- Self-adhesive preparation of extruded plastic and cover profiles for permanent mounting in the furniture industry
- Mounting of decorative parts and stay bars
- Fastening of face plates, holders and cable ducts
- Mounting of exterior and interior mirrors in plastic housings in the automotive industry

### Product features

### Applicability on

Initial adhesion (tack)	● ● ●	Foam	● ○ ○
Final adhesion	● ● ○	Rubber	● ○ ○
Dimensional stability	● ● ●	Fabric	● ● ●
Adhesion on even surfaces	● ● ●	Glass/Ceramics	● ● ●
Adhesion on rough surfaces	● ● ●	Wood	● ● ●
Ageing resistance	● ● ○	High energy plastics: PVC, PC, ABS,...	● ● ●
Weathering resistance	● ● ○	Low energy plastics: PE, PP,...	● ○ ○
Chemical resistance	● ● ○	Metal	● ● ●
Resistance to plasticizers	● ● ○	Paper/Cardboard	● ● ●

● ● ● very suitable

● ● ○ suitable

● ○ ○ suitable with reductions

○ ○ ○ not suitable

Art. No. 11 731 I 01

## Double-sided pressure sensitive adhesive mounting tape

### Specific technical data\*

Adhesive strength in accordance with DIN EN 1939 after 24 hours at room temperature on different substrates:

Soft-PVC	26 N/25 mm
Polypropylene	26 N/25 mm
Polyethylene	20 N/25 mm
PTFE	6 N/25 mm
Hard-PVC	42 N/25 mm
Glass	44 N/25 mm
Steel	45 N/25 mm

Rising heat test at 1 kg strength, beginning at 30 °C, increasing of temperature every 30 minutes by 10 °C


100 °C

\* Specific test results, statistically not approved.

Art. No. 11 731 | 01

## Double-sided pressure sensitive adhesive mounting tape

Technical Data		
<b>Shear strength</b>	on steel according to DIN EN 1943, edition 1996, at +23 °C +/- 2°C	60 N/625 mm <sup>2</sup>
<b>Peel strength</b>	on steel according to DIN EN 1939, edition 1996, at +23 °C +/- 2°C	37 N/25 mm
<b>Temperature range</b>		-40 °C to + 80 °C



Application	
<b>Recommended application temperature</b>	18 °C to 35 °C
<b>Application guidelines</b>	<a href="http://www.lohmann-tapes.com">www.lohmann-tapes.com</a>

Storage
Adhesive tapes should be stored at room temperature and normal humidity (50 – 70%). The storage stability is one year after delivery.

Product presentation								
Converted product	Rolls			Spools				
<b>Width [mm]</b>	> 6	> 15	> 19	4-6	7-8	9-14	15	19
<b>Length [m]</b>	50/100	200	300	5000	4000	3000	2000	1500
<b>Max. log width: 1200 mm</b>	Other dimensions, die-cuts and sheets on request							

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.

Variants	Duplocoll® 371			Duplocoll® 373	
	Name	Thickness [mm]		Name	Thickness [mm]
<b>Liner</b>	Polyethylene film yellow	0,08		Silicone paper yellow	0,09
<b>Adhesive covered side</b>	Modified acrylic	0,23		Modified acrylic	0,33
<b>Carrier</b>	PVC film white			Polypropylene film white	
<b>Adhesive open side</b>	Modified acrylic			Modified acrylic	

The physical characteristics contained in our data sheets represent typical or average values. They do not represent any warranties or guarantees and must not be used for technical specification purposes. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. The buyer is responsible for determining the suitability of the specific tape for its intended use in connection with user's method of application. Please consult our Technical Applications Department for specific advice. Our general Term and Conditions of Sale apply, particularly with regard to warranty and liability.

Date of issue: April 2004

LOHMANN GmbH & Co. KG  
 Pressure Sensitive Adhesive Tapes Division  
 Postfach 14 54 • D-56504 Neuwied  
 Tel. + 49 (0) 26 31 34 - 0  
 Fax + 49 (0) 26 31 34 - 6661  
 E-mail: klebebandsysteme@lohmann-gruppe.de

For further information  
[www.lohmann-tapes.com](http://www.lohmann-tapes.com)

